90+|素色肌肤砖



90+|素色肌肤砖

广东省佛山市禅城区塑宝西路60号 欧洲工业园二座二层自编之C区 C Area, Level 3, Building 2, European Industrial Park, No.60. West Langbao Road, Foshan City,

















PROUCTFEATURE SURFACE APPLICATION INSTALLATION GUIDANCE











## **COLOURS**



Off-white 60TL20R 600x600mm



Off-white 612TL20URD



Silver Grey **60TL21R** 600x600mm



Silver Grey 612TL21URD



**60TL22R** 600x600mm



Ivory 612TL22URD

## PRODUCT FEATURE/SURFACE APPLICATION/INSTALLATION GUIDANCE




















V1=Uniform Appearance V3=Moderate Variation

V2=Slight Variation V4=Substantial Variation

## **TECHNICAL SPECIFICATION**

Dimensions & Surface Quality Length and Width	$\pm$ 0.6% max.	-0. 03-0.03%	-0. 03-0.03%
Thickness	±5% max.	9.0-9.5mm	11.0-11.5mm
90° Orthogonality	±0.5% max.	-0. 06-0.07%	-0. 06-0.07%
Straightness of sides	±0.5% max.	-0. 06-0.07%	-0. 02-0.03%
Surfaces flatness	±0.5% max.	-0. 05-0.07%	-0. 09-0.11%
Physical Properties  Water absorption	≤0.5%	≤0.5%	≤0.5%
Breaking strength	≥1300N	2265N	4031N
→ Bending resistance	≥35N/mm²	38N/mn²	40N/mm²
Resistance to deep abrasion	≤175mm³	Class 4	Class 4
Temperature shock resistance	No visible crack	No visible crack	Durable
Resistance to frost	No visible crack	No visible crack	No visible crack
Non-slip	R9-R11	RII	RII
Colour resistance to light	no colour changes	no colour changes	no colour changes
Chemical Properties  Chemical resistance	no visible changes when subjected to chemicals	Durable	Durable
Resistance to staining	≥3	Class 5	Class 5

## **PACKING DETAILS**

